



## PRODUCT DATA

**Brand Name:** 22 CAULK

**Description:** 22 CAULK is ideal for filling joints and cracks in refractory linings. Job site mixing is not needed. Just snip-off the tip of the ready-to-use caulking tube and apply the moist material using a hand or air powered caulking gun. Heat loss through joints and cracks will be reduced. Fine particles will not accumulate in those openings, preventing further damage to the lining. The surface of 22 CAULK will harden when exposed to air.

Physical properties shown are average values of samples taken under controlled conditions  
ASTM test methods used where applicable

**Maximum Service Temperature:** 3000°F (1650°C)

**Moisture Content :** Approximately 18%

### Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	86.5
Phosphorus Pentoxide (P <sub>2</sub> O <sub>5</sub> ) .....	13.3
Alkalis (Na <sub>2</sub> O+K <sub>2</sub> O) .....	0.2

**Standard Packaging:** Standard Caulking Tube, 12 Tubes per Case

Brand Code: 0101

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/25/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505