



PRODUCT DATA

Brand Name: EZ CAST[®] 2800

Description: EZ CAST[®] 2800 is similar to EZ CAST[®] 2700, except designed for applications up to 2800°F. In the laboratory, this product has tested well for resistance to CO (carbon monoxide) disintegration encountered in coke ovens and blast furnaces.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 2800°F (1538°C)

Typical Water Required for Mixing (by weight) :

Vibration Casting	4.5 - 6.0%
Self Flow Casting	7.0 - 8.3%

Dry Material Required per Cubic Foot:

Vibration Casting	139 - 145 lbs
Self Flow Casting	136 - 140 lbs

	Vibration Casting Data		Self Flow/Pump Casting Data	
Bulk Density (pcf)				
After 220°F (105°C)	144 - 150	(2.30 - 2.40 g/cm ³)	141 - 145	(2.26 - 2.32 g/cm ³)
After 1500°F (815°C)	139 - 145	(2.22 - 2.32 g/cm ³)	136 - 140	(2.18 - 2.24 g/cm ³)
Cold Crushing Strength (psi)				
After 220°F (105°C)	12000 - 18000	(840 - 1260 kg/cm ²)	7000 - 11000	(490 - 770 kg/cm ²)
After 1500°F (815°C)	7000 - 13000	(490 - 910 kg/cm ²)	5000 - 8000	(350 - 560 kg/cm ²)
Modulus of Rupture (psi)				
After 220°F (105°C)	1400 - 1800	(98 - 126 kg/cm ²)	1400 - 1800	(98 - 126 kg/cm ²)
After 1500°F (815°C)	1200 - 1600	(84 - 112 kg/cm ²)	900 - 1300	(63 - 91 kg/cm ²)
Apparent Porosity (%)				
After 220°F (105°C)	7 - 10		10 - 12	
After 1500°F (815°C)	14 - 16		17 - 19	
Permanent Linear Change (%)				
After 1500°F (815°C)	-0.2 to 0.0		-0.2 to 0.0	

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	48.0
Silica (SiO ₂)	45.8
Lime (CaO)	2.9
Iron Oxide (Fe ₂ O ₃)	0.9
Titania (TiO ₂)	2.0
Phosphorus Pentoxide (P ₂ O ₅)	0.1
Alkalies (Na ₂ O+K ₂ O)	0.3

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 0809

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

12/20/16 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.