



PRODUCT DATA

Brand Name: KRICON® 30

Description: KRICON® 30 is a low iron castable with good slag resistance up to 3000°F

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 3000°F (1649°C)

Typical Water Required for Mixing (by weight) :

Vibration Casting 4.5 to 6.0%

Vibration Cast Data

Bulk Density (pcf)

After 220°F (104°C)	142 - 152	(2.27 - 2.43 g/cm ³)
After 1500°F (815°C)	144 - 150	(2.31 - 2.40 g/cm ³)
After 2000°F (1093°C)	143 - 149	(2.29 - 2.39 g/cm ³)

Cold Crushing Strength (psi)

After 220°F (104°C)	6000 - 12000	(420 - 840 kg/cm ²)
After 1500°F (815°C)	6700 - 12700	(469 - 889 kg/cm ²)
After 2000°F (1093°C)	5300 - 11300	(371 - 791 kg/cm ²)

Modulus of Rupture (psi)

After 220°F (104°C)	1200 - 2200	(84 - 154 kg/cm ²)
After 1500°F (815°C)	1100 - 2100	(77 - 147 kg/cm ²)
After 2000°F (1093°C)	1400 - 2400	(98 - 168 kg/cm ²)

Thermal Conductivity (K Factor)

	<u>BTU/ft²/hr/°F/inch</u>	<u>W/mK</u>
After 1500°F (815°C)	13.4	1.93
After 2000°F (1093°C)	14.8	2.13

Permanent Linear Change (%)

After 1500°F (815°C)	-0.5 to 0.1
After 2000°F (1093°C)	-0.6 to 0.0

Apparent Porosity (%)

After 1500°F (815°C)	10 - 14
After 2000°F (1093°C)	10 - 14

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	46.5
Silica (SiO ₂)	45.4
Lime (CaO)	1.2
Iron Oxide (Fe ₂ O ₃)	1.2
Titania (TiO ₂)	1.9
Magnesia (MgO)	0.3
Alkalis (Na ₂ O+K ₂ O)	0.7

Standard Packaging: 55 lb bag. 72 bags per pallet. Bulk packaging available.

Brand Code: 0951

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/19/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.