



PRODUCT DATA

Brand Name: KRILEX® 50

Description: KRILEX® 50 has good chemical corrosion resistance, high hot strength and moderately low porosity. It is most often recommended for use in the lower checkers and superstructure of glass furnace regenerators. It is also used in reverberatory, converting and flash smelting furnaces in the non-ferrous metals industry where its alkali resistance and lower MgO content is beneficial.

Physical properties shown are averages based on standard brick sizes.
ASTM test methods used where applicable

Bulk Density (pcf)

As Received 193 (3.09 g/cm³)

Modulus of Rupture (psi)

At 70°F (21°C) 800 (56 kg/cm²)

Cold Crushing Strength (psi)

At 70°F (21°C) 3560 (249 kg/cm²)

Apparent Porosity (%)

As Received 18.4

Typical Chemical Analysis (%)

(Calcined Basis)

Magnesia (MgO)	54.4
Chromic Oxide (Cr ₂ O ₃)	21.9
Iron Oxide (Fe ₂ O ₃)	13.4
Silica (SiO ₂)	1.7
Lime (CaO)	1.0
Alumina (Al ₂ O ₃)	7.6

Brand Code: 1360

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/19/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.