



# PRODUCT DATA

**Brand Name:** **OXILINE H**  
**Description:** BURNED HIGH PURITY MAGNESITE BRICK

Physical properties shown are averages based on standard brick sizes.  
ASTM test methods used where applicable

**Bulk Density (pcf)**

As Received 182 (2.92 g/cm<sup>3</sup>)

**Modulus of Rupture (psi)**

At 70°F (21°C) 1830 (128 kg/cm<sup>2</sup>)

**Apparent Porosity (%)**

As Received 16.1

**Typical Chemical Analysis (%)**

(Calcined Basis)

Magnesia (MgO) .....	98.0
Silica (SiO <sub>2</sub> ) .....	0.6
Alumina (Al <sub>2</sub> O <sub>3</sub> ) .....	0.1
Lime (CaO) .....	1.2
Iron Oxide (Fe <sub>2</sub> O <sub>3</sub> ) .....	0.1

Brand Code: 2521

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESOCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/20/17 is the date that this data sheet was updated. Check with your RESOCO sales representative or RESOCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505