



PRODUCT DATA

Brand Name:

Description: QUIKLITE 8PC is a high strength, medium weight castable formulated to be installed by pumping or shotcreting methods. After the initial set, this unique insulating castable can be initially heated without using the traditional ramp-and-hold heatup schedule. Refer to the recommended QUIKTURN heatup schedule for initial heatup. For shotcreting, use RESCO SC-1 activator.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Service Temperature: 2800°F (1540°C)

Typical Water Required for Mixing (by weight) :

Pump Cast 27.0%

Pump Cast Data		
Bulk Density (pcf)		
After 1500°F (815°C)	85	(1.36 g/cm ³)
Cold Crushing Strength (psi)		
After 1500°F (815°C)	950	(67 kg/cm ²)
Thermal Conductivity (K Factor)	BTU/ft ² /hr./°F/inch	W/mK
500°F (260°C)	2.5	0.36
1000°F (538°C)	2.7	0.39
1500°F (815°C)	2.8	0.41
Permanent Linear Change (%)		
220°F (105°C) to 1500°F (815°C)	-0.3 to 0.0	
Typical Chemical Analysis (%) (Calcined Basis)		
Alumina (Al ₂ O ₃)	40.2	
Silica (SiO ₂)	49.1	
Lime (CaO)	8.0	
Iron Oxide (Fe ₂ O ₃)	0.6	
Titania (TiO ₂)	0.5	
Magnesia (MgO)	0.2	
Alkalies (Na ₂ O+K ₂ O)	1.5	

Standard Packaging: 50 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code: 1645

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/06/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.