



PRODUCT DATA

Brand Name: R 85 DV

Description: RESCO's R 85 DV is a Heat-Setting, 80% Alumina, Dry Vibratable Mix that is used primarily in the steel industry. This product is slightly tempered to control dusting. R-85 DV is installed by pneumatic ramming methods.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

Maximum Grain Size : 8 mesh (2.38 mm)

Minimum Sintering Temperature : 1500°F (815°C) approximate

Dry Material Required per Cubic Foot : 155 - 160 lbs. (approximate)

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	82.2
Silica (SiO ₂)	10.3
Lime (CaO)	0.2
Iron Oxide (Fe ₂ O ₃)	1.3
Titania (TiO ₂)	3.2
Magnesia (MgO)	0.2
Alkalies (Na ₂ O+K ₂ O)	0.3
Others	2.3

Standard Packaging: 60 lb bag. 50 bags per pallet. Bulk packaging available.

Brand Code: 3201

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

03/07/17 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.