



PRODUCT DATA

Brand Name:

RESCAL 90XD/C

Description:

Burned, 90% ALUMINA BRICK and SHAPES

Physical properties shown are average values based on testing samples prepared under controlled conditions

Bulk Density (pcf)

As Received 188 (3.01 g/cm³)

Apparent Porosity (%)

As Received 14.5

Modulus of Rupture (psi)

At 70°F (21°C) 3,925 (276 kg/cm²)

Cold Crushing Strength (psi)

At 70°F (21°C) 16,250 (1142 kg/cm²)

Permanent Linear Change (%)

2550°F (1400°C) / 5 Hours +0.1

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	93.6
Silica (SiO ₂)	4.4
Iron Oxide (Fe ₂ O ₃)	0.1
Other	1.9

Brand Code: 3851

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

08/05/19 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505