



PRODUCT DATA

Brand Name: RESCOBOND DRY BRUSH MIX

Description: Rescobond Dry Brush Mix is a dry material that when mixed with water is ideal for strengthening existing refractory lining surfaces. It can be applied up to ¼" thick providing increased refractory protection without a great loss of volume to your unit. Additional water can be added to adjust the consistency. It can be applied with a brush, trowel, rubber float, roller, sprayer, etc. It hardens in air and becomes non-hygroscopic when heated to only 250 - 300°F.

Physical properties shown are average values of samples taken under controlled conditions
ASTM test methods used where applicable

<u>Water Addition</u>	Hobart	10.0 wt%
	Drill Mixer	13.0 wt%

Application: One 16 pound pail will cover approximately 4.5 square feet at a thickness of ¼ inch (6 mm)

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	86.5
Phosphorus Pentoxide (P ₂ O ₅)	13.2
Others	0.3

Standard Packaging: 65 lb. pails. 48 pails per pallet

Brand Code: 0072

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

08/16/2022 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505