



PRODUCT DATA

Brand Name: **SENECA 80XD**
Description: BURNED, HIGH ALUMINA BRICK

Physical properties shown are averages based on standard brick sizes.
ASTM test methods used where applicable

Bulk Density (pcf)

As Received 173 (2.77 g/cm³)

Modulus of Rupture (psi)

At 70°F (21°C) 2100 (148 kg/cm²)

Cold Crushing Strength (psi)

At 70°F (21°C) 9600 (672 kg/cm²)

Apparent Porosity (%)

As Received 15

Permanent Linear Change (%)

After 2910°F (1600°C) +2.5

Typical Chemical Analysis (%)

(Calcined Basis)

Alumina (Al ₂ O ₃)	79.8
Silica (SiO ₂)	13.7
Iron Oxide (Fe ₂ O ₃)	1.8
Lime (CaO)	0.1
Titania (TiO ₂)	2.7
Magnesia (MgO)	0.1
Phosphorus Pentoxide (P ₂ O ₅)	1.4
Alkalis (Na ₂ O+K ₂ O)	0.4

Brand Code: 2923

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

02/02/2021 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.