



PRODUCT DATA

Brand Name: **MAXLINE 13 NFY**
Description: RESIN BONDED, FUSED GRAIN MAGNESIA-CARBON BRICK

Physical properties shown are averages based on standard brick sizes.
ASTM test methods used where applicable

Bulk Density (pcf)

As Received	184	(2.95 g/cm ³)
After Coking	178	(2.88 g/cm ³)

Modulus of Rupture (psi)

At 70°F (21°C)	1600	(127 kg/cm ²)
----------------	------	---------------------------

Coked Porosity (%)

After Coking	11.0
--------------	------

Total Carbon (%)

After Coking	13
--------------	----

Typical Chemical Analysis (%)

(Calcined Basis)

Magnesia (MgO)	96.8
Silica (SiO ₂)	0.8
Alumina (Al ₂ O ₃)	0.2
Lime (CaO)	1.7
Iron Oxide (Fe ₂ O ₃)	0.5

Brand Code: 7482

The properties shown on this data sheet represent typical average results using standard ASTM test methods (unless otherwise noted) conducted under controlled condition (using standard rectangular shapes), and should not be considered to be guaranteed specifications. Properties are subject to normal manufacturing statistical standard deviation ranges, and Resco Products, Inc. reserves the right to modify the properties and specifications at any time without prior notice.

RESCO PRODUCTS disclaims any express or implied warranties based on this sheet.

01/18/2023 is the date that this data sheet was updated. Check with your RESCO sales representative or RESCO website to determine you have the current sheet.

One Robinson Plaza - Suite 300, 6600 Steubenville Pike, Pittsburgh, PA, 15205 Phone: 888-283-5505